ROMATT 2002

DESCRIPTION

Formulated to EGYPTIAN **STANDDERD SPECIFICATIONS** and Romatt 2002 based on modified alkyd and pigmented.A matt alkyd paint for interior and exterior uses to be applied as a top coat or under coat for ROOTS PAINTS company alkyd system with the following advantages:

- Good color retention.
- Good impact resistance.
- Easy to clean.

TECHNICAL DATA :

- Finish, color : matt, As the customer request.
- Solid by volume : 59 % (approx.)
- Specific gravity : 1.49.
- Theoretical spreading rate : 8 m2/Kg (50 microns D.F.T.)
- Dry film thickness : 50 microns
- wet film thickness : 110 microns.
- Thinner : Roots thinner No. RO1001.
- Drying time (Surface) : 1 – 2 Hrs. (at 25 °C& 60% R .H)
  Full cured : 7 days (at 25 °C & 60% R .H)
- Recoat interval
  Min : 12hrs (at 25 °C & 60% R. H)
  Max : No limitation
- Shelf life : 12 months (at normal conditions in original containers.
- Packing : 25 Kgm.

SURFACE PREPARATION :

The surface must be dry and clean from dirties, oils and greases, and it is applied on primed metal surface.

APPLICATION METHODS : By brush, roller and air spray.